

钢号:	GCr15									
对应钢种及化学元素:	标准/钢种	化学元素/Chemical Composition(%)								
	Standard/Steel Grade	C	Si	Mn	Cr	Mo	Ni	P	S	
	GB/T 18254	GCr15	0.95-1.05	0.15-0.35	0.25-0.45	1.40-1.65	≤0.10	≤0.30	≤0.025	≤0.025
	ASTM A295	52100	0.93-1.05	0.15~0.35	0.25-0.45	1.35-1.60	≤0.10	≤0.25	≤0.025	≤0.015
	DIN EN ISO 683/17	100Cr6	0.93-1.05	0.15-0.35	0.25-0.45	1.35-1.60	≤0.10	-	≤0.025	≤0.015
	JIS G4805	SUJ2	0.95-1.10	0.15~0.35	≤0.50	1.30-1.60	≤0.08	+Cu≤0.25	≤0.025	≤0.025
简介:										
形状及尺寸:	Φ 200-600mm									
交货条件:	电炉+精炼+真空脱气, 热轧/锻造, 正火, 黑皮/车光									
备注:										

钢号:	GCr15SiMn									
对应钢种及化学元素:	标准/钢种	化学元素/Chemical Composition(%)								
	Standard/Steel Grade	C	Si	Mn	Cr	Mo	Ni	P	S	
	GB/T 18254	GCr15SiMn	0.95-1.05	0.45-0.75	0.95-1.25	1.40-1.65	≤0.10	≤0.30	≤0.025	≤0.025
	DIN EN ISO 683/17	100CrMnSi6-4	0.93-1.05	0.45-0.75	1.00-1.20	1.40-1.65	≤0.10	-	≤0.025	≤0.015
简介:										
形状及尺寸:	Φ 200-600mm									
交货条件:	电炉+精炼+真空脱气, 热轧/锻造, 正火, 黑皮/车光									
备注:										